



Butyl Products Ltd.

11 Radford Crescent, Billericay, Essex CM12 0DW, England.

Tel: +44 (0)1277 653281 Fax: +44 (0)1277 657921

E-mail: enquiries@butylproducts.co.uk www.butylproducts.co.uk



1.25mm Scrim Reinforced EPDM

Properties	Test Method	Specification Typical	Minimum Values
Fabric type		SS0 Decitex polyester	
Tensile Strength (warp and weft)	BS 3424 Part 4	-----	500 N / 50mm
Elongation at Break (warp and weft)	BS 3424 Part 4	25%	20% Rubber only 300%
Tear strength (rubber coating)	BS 903 Part A3	30 N / mm	25 N / mm
Ozone resistance (rubber coating) (7 days/50pphm/30°C)	BS 903 Part A43 Procedure A	-----	50% extensions No cracks
Heat ageing (retentions) (rubber coating) (7 days @ 100°C)	BS 903 Part A19	6.0 Mpa 250%	5.6 Mpa 200%
Flex cracking	BS 903 Part A10		200.000 cycles, no crack
Nominal weight		1820g/m ²	-----
Dimensional Stability	1 hr. @ 100°C	+/- 1% max.	-----
Operating Temperature Range	ISO188:1998	-40°C to +130°C	-----
Bursting strength	BS 3424 Part 6	1200 KN/m ²	-----

The information herein is based upon data obtained by the manufacturer and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.